

NOTICE: When government or other drawings, specifications or other data are used for any purpose other than in connection with a definitely related government procurement operation, the U. S. Government thereby incurs no responsibility, nor any obligation whatsoever; and the fact that the Government may have formulated, furnished, or in any way supplied the said drawings, specifications, or other data is not to be regarded by implication or otherwise as in any manner licensing the holder or any other person or corporation, or conveying any rights or permission to manufacture, use or sell any patented invention that may in any way be related thereto.

63-3-2

TR-1102

401 3819


FLUID AMPLIFICATION

Use of Epoxy Castings for Fluid Amplifier Design

David S. Marsh

Edward V. Hobbs

11 February 1963



HARRY DIAMOND LABORATORIES
FORMERLY: DIAMOND ORDNANCE FUZE LABORATORIES
ARMY MATERIAL COMMAND
WASHINGTON 25, D. C.

HARRY DIAMOND LABORATORIES

Robert W. McEvoy
LtCol, Ord Corps
Commanding

B. M. Horton
Technical Director

MISSION

The mission of the Harry Diamond Laboratories is:

(1) To perform research and engineering on systems for detecting, locating, and evaluating targets; for accomplishing safing, arming, and munition control functions; and for providing initiation signals: these systems include, but are not limited to, radio and non-radio proximity fuzes, predictor-computer fuzes, electronic timers, electrically-initiated fuzes, and related items.

(2) To perform research and engineering in fluid amplification and fluid-actuated control systems.

(3) To perform research and engineering in instrumentation and measurement in support of the above.

(4) To perform research and engineering in order to achieve maximum immunity of systems to adverse influences, including counter-measures, nuclear radiation, battlefield conditions, and high-altitude and space environments.

(5) To perform research and engineering on materials, components, and subsystems in support of above.

(6) To conduct basic research in the physical sciences in support of the above.

(7) To provide consultative services to other Government agencies when requested.

(8) To carry out special projects lying within installation competence upon approval by the Director of Research and Development, Army Materiel Command.

(9) To maintain a high degree of competence in the application of the physical sciences to the solution of military problems.

The findings in this report are not to be construed as an official Department of the Army position.

UNITED STATES ARMY MATERIEL COMMAND
HARRY DIAMOND LABORATORIES
WASHINGTON 25, D.C.

DA-5N03-01-003
OMS 5010.11.71200
HDL Proj. 31100

TR-1102

11 February 1963

FLUID AMPLIFICATION

8. Use of Epoxy Castings for Fluid Amplifier Design

David S. Marsh

Edward V. Hobbs

FOR THE COMMANDER:
Approved by

RD Hatcher
R. D. Hatcher
Chief, Laboratory 300

Qualified requesters may obtain copies of this report from ASTIA.

CONTENTS

	Page No.
ABSTRACT.	5
1. INTRODUCTION	5
2. BACKGROUND	6
3. EPOXY CASTING PROCESS.	6
3.1 Basic Process	6
3.2 Design Study of a Modified AND Unit	7
4. OTHER ADVANTAGES EPOXY CASTING PROCESS.....	8
5. CONCLUSION	9
ACKNOWLEDGEMENT	9

ABSTRACT

An adjustable master unit has been used to make series of cast-epoxy fluid amplifiers that incorporate incremental dimensional changes. Subsequent unit testing identifies the best geometry for a given performance requirement. The process provides an inexpensive means of precisely producing the numerous units necessary for empirical design studies.

The basic rubber mold and epoxy casting process is described, as well as the adjustment of the master unit. Some other uses of epoxy castings in the fluid amplifier field are also described.

1. INTRODUCTION

In the design of fluid amplifiers, the most widely used approach at present is to take a current design that has some of the desired characteristics and to modify the geometry of the unit in increments. The design is tested after each change, and those changes that move unit performance in the desired direction are retained and followed up. Although this process can be greatly aided by water table studies, it is time consuming at best.

The ideal device for empirical design studies, perhaps, would be one in which all of the component parts are mounted on micrometer heads. With such a unit, the parts could then be precisely moved with the device in operation and the desired design could be "tuned-in." Such an approach was tried early in the program of fluid amplification development at Harry Diamond Laboratories, but sealing problems were never fully solved. Even when this unit was firmly clamped during tests, and unclamped to move the parts, leakage was still a problem.

One effective answer to the leakage problem is the one currently in use in metal units: the passages are formed in a solid piece of material, and the top surface is sealed to a cover plate.

A basic requirement for empirical design work as it has developed at HDL, then, is a series of configurations, each slightly different from the others which can be effectively sealed. Some idea of the number of different configurations to be tested in a program comes from a consideration of the number of parameters involved. In even a small program there may be as many as eight variables: length, setback, and angle of each of two walls, and downstream and transverse position of the splitter. In view of the number of units that may be necessary, a method of producing them in quantities of tens or dozens at low cost is required.

2. BACKGROUND

Methods of producing passages in a solid material that have been considered include conventional machining, etching in glass and plastic, injection molding, and epoxy casting.

In conventional machining, if a separate unit is made to incorporate each design change, valuable shop time is used in great amounts. In addition, successive units may vary slightly in those dimensions that should have remained unchanged. While not often serious, such changes add an unknown factor to the analysis of test data. To assure that only the desired dimensions are changed, sometimes only one unit is built. This unit is then tested, disassembled, modified, reassembled, and retested. This process takes less shop time than does the construction of separate units, but only a limited number of variations can be made on one unit. In addition, if the desired configuration is passed, it is usually not practical to "back up" and re-examine it. In any event, the number of combinations possible in such a study makes any process that involves machine work on each unit prohibitive in both time and money.

Both glass and plastic etching processes start with optical steps, so that design changes involve only changing an original drawing. Both, however, produce passages that narrow with depth. In the plastic-etch process, the bottoms of the passages are smooth, since they are actually the top surface of a metal base plate. Passages in the glass units, however, are somewhat rough on the bottom and sometimes show a slight "grain". Glass units must be handled with care and are not easily modified.

Injection molding has also been used, but it is more suited to large production runs after a design has been fixed.

3. EPOXY CASTING PROCESS

The epoxy casting process produces a one-piece unit quickly and at low cost. With a suitable master unit, the design can be changed quickly and easily.

3.1 Basic Process

The basic process of making plastic duplicates of an item, with the intermediate step of a rubber mold, is not new. The item to be duplicated is placed within a suitable form, which may be merely blocks of wood or metal arranged on a flat surface to contain the liquid rubber. The liquid, a silicone rubber compound that vulcanizes at room temperature, is then poured over and around the master. A vacuum at this time is helpful in removing bubbles of entrained air from the rubber. The rubber penetrates quite well into the surface details of the master. Vulcanizing time depends on heat and the curing agent used. It ranges from a few to 48 hr. When vulcanized, the mold

is still sufficiently flexible and elastic to be removed from the master without great difficulty. The mold is examined after its removal from the master, and "flash" is trimmed off. Gross modifications may be carved into it at this time. When the mold is fully prepared, epoxy compound is poured in. Bubbles are removed from the epoxy either mechanically, with a pick or brush, or by means of a vacuum. After the epoxy has cured, the piece is removed from the mold. Here, again, the elasticity and flexibility of the rubber allow pieces to be removed which have no draft. With little or no further work, the resulting piece accurately duplicates the desired features of the original item.

3.2 Design Study of a Modified AND Unit

The casting process is now being applied in the design of a modified "and" unit for use in a binary adding machine. The unit has only one control jet. There is to be flow at one output when there is power and control jet pressure; with the control pressure removed but with the control passage still open, flow is to return to the opposite (control side) output.

The object of the design study is to determine the combination of wall angles, wall setbacks, and splitter position that will produce the desired flow behavior. A series of epoxy units is being made which incorporate incremental changes in the variables; testing of the units will show which configuration is best.

A special adjustable master has been made for this work (fig. 1 and 2). Since the design changes involve only the walls and splitter, these pieces are separate and movable. The power jet and most of the control jet were machined into a base plate. Most of the area usually occupied by the walls and splitter was routed out to the same depth as the power and control chambers, leaving a rim around the outer edge. The aspect ratio in the master is somewhat greater than that desired in the casting to allow for the removal of some material when the surface of the casting is smoothed. The nozzle width is 0.030 in. (Passages as narrow as 0.010 in. have been duplicated successfully.) The walls can be set back as required. With the wall parts shown, the wall angles are 0 deg on the left (control side), 16 deg on the right. The splitter angle is 5 deg.

When the movable parts of the master are in their desired locations, they are secured with C-clamps. Melted wax is then allowed to flow into the region between the wall pieces and the rim of the base plate. The wax flows under and between all of the movable parts, holding them in place and sealing any spaces between them against penetration by the rubber of the mold. The resulting wax fillets in the passages are scraped out before pouring the mold material.

After the casting is made, the top surface is smoothed by using wet sandpaper on a surface plate. Vacuum grease is used as a seal for the top plate. Since this program involves the testing of many units, the necessary fittings are installed in a cover plate that remains connected to the test setup. Units to be tested are then clamped to the top plate, so that a new unit may be easily and quickly connected to the rig. For more permanence, the cover can be secured in the usual manner with screws tapped into the epoxy or the cover, or the cover can be bonded in place to produce what amounts to a one-piece unit.

If the master is arranged for a new design in the morning, the mold can be ready the following day, releasing the master for another modification. The test piece can be available in the afternoon of the third day. In the normal investigation, new units can be made faster than they can be evaluated.

The splitter is not incorporated in the casting when its position is being evaluated. Instead, the number of castings is reduced somewhat by using a separate, movable splitter that can be clamped in place with the cover plate. When other parameters are being studied, however, the splitter is incorporated in the castings so that it will be in an identical position throughout a series of tests.

With such a system, a broad and rapid survey of an interesting range of dimensional changes is made. After this survey is made, it is possible to go back to an interesting part of the range for a more detailed evaluation of smaller increments.

4. OTHER ADVANTAGES EPOXY CASTING PROCESS

Once the optimum geometry is found, the process can be used to duplicate units indefinitely and with considerable uniformity and accuracy from copy to copy. If the mold becomes damaged, second and third generation molds can be made from the epoxy pieces with little or no loss of detail.

As a material for use in this work, epoxy has several desirable properties. It can be machined if necessary. It can be permanently bonded to other epoxy pieces, such as cover plates, or to itself if a unit should be broken. It can be made with different degrees of softness in each of several layers. Using this last feature, cover plates have been made which have a soft bottom surface that serves as a self-gasket and that have the connecting fittings molded in place (fig. 3).

In addition to the basic design study described above, this process has been used where machined modifications of a basic unit were required. For example, a study of different bleed passage configurations in a standard brass bistable unit was made as follows: Two epoxy units

were made--one for a study of vortex bleeds, the other for a study of strongly diverging bleed passages (fig. 4). The machinability of epoxy is important in this work. Also of importance is the fact that the units are identical in all respects except for the bleed machining, since they began as duplicates of the same metal unit.

A three-stage counter originally etched in glass has also been duplicated in epoxy to obtain a unit in a material that could be machined. An additional benefit is that the casting is less fragile than the original. In the intermediate step, mold ridges, representing channels, were removed or changed to alter the channels in the epoxy (fig. 5).

5. CONCLUSION

The epoxy casting process is a valuable tool in the empirical design and small-scale production of fluid amplifier units. It provides exact, leak-free duplicates of a master unit. These castings can be machined, are rugged and low in cost, and can be made in a short time.

ACKNOWLEDGEMENT

The castings described were made by John W. Tidler. His patience and skill were essential in making this design technique a success.






Figure 1. Adjustable master unit.




Adjustable master and form



Mold



Rough casting



Finished casting



Unit clamped to cover

Figure 2. Steps in epoxy casting process using adjustable master.




Figure 3. Cover plate mold and casting.





Figure 4. Bistable units with bleed passages.



Modified mold



Rough casting - modified



Rough casting - unmodified



Finished duplicate unit

Figure 5. Three-stage counter.

DISTRIBUTION

Director
Advanced Research Projects Agency
Washington 25, D. C.
ATTN: Fred A. Koether

Office of the Dir. of Defense
Research and Engineering
The Pentagon, Washington 25, D. C.
ATTN: Tech Library (Rm 3C128)

Deputy Ass't Secretary of the Army
Research & Development
Washington 25, D. C.
ATTN: Mr. W. S. Hinman, Jr.
Rm 3E390, Pentagon Bldg.

Commanding General
Army Materiel Command
Physics and Electronics Branch
Washington 25, D. C.
ATTN: AMCRD-RS, Major W. Kerttula

Commanding General
Army Materiel Command
Washington 25, D. C.
ATTN: AMCRD-DE-N

Commanding General
US Army Materiel Command
Washington 25, D. C.
ATTN: AMCRD-DE-MI

Commanding General
Army Materiel Command
Washington 25, D. C.
ATTN: R & D Directorate,
AMCRD-RS-CM

Commanding General
Army Munitions Command
Dover, New Jersey
ATTN: Technical Library

Commanding Officer
US Army Munitions Command
Frankford Arsenal
Philadelphia 37, Pennsylvania
ATTN: Librarian, #0270

Commanding Officer
Army Research Office - Durham
Box CM. Duke Station
Durham, N. C.

Commanding Officer
Artillery Combat Dev. Agency
Fort Sill, Okla

Commanding Officer
US Army Biological Lab
Fort Detrick
Frederick, Maryland
ATTN: Tech Library

Commanding General
Engr Research & Dev Lab
Fort Belvoir, Va
ATTN: Tech Library

Commanding Officer
US Army Limited War Lab
Aberdeen Proving Ground, Md
ATTN: Lt Col J.T. Brown

Department of the Army
Office of the Chief of R&D
Washington 25, D. C.
ATTN: Chief, Combat
Material Div

Director, Special Weapons
Office of the Chief of R&D
Department of the Army
Washington 25, D. C.

Department of the Army
Office, Chief of R&D
Physical Science Div
Washington 25, D. C.
ATTN: Dr. R. B. Watson

Commanding Officer
Picatinny Arsenal
Dover, New Jersey
ATTN: Tech Library - 3 copies

DISTRIBUTION (Cont'd)

Redstone Scientific Info Center
US Army Missile Command
Redstone Arsenal, Alabama
ATTN: Chief, Document Sec - 10 copies

Redstone Arsenal
Redstone Arsenal, Alabama
ATTN: Charles Schriener,
ORDXM-REE Bldg. 7446

Commanding Officer
Rock Island Arsenal
Technical Information Branch
Rock Island, Ill

Commanding Officer
US Army Weapons Comd
Springfield Armory
Springfield, Mass
ATTN: TIU

Commanding Officer
US Army Materials Research Agency
Watertown Arsenal
Watertown 72, Mass
ATTN: Tech Info Center

Commanding Officer
Watervliet Arsenal
Watervliet, New York
ATTN: Tech Library B-C

Commanding General
White Sands Missile Range
White Sands, N. M.
ATTN: Tech Library

Department of the Navy
Bureau of Naval Weapons
Washington 25, D. C.
ATTN: S. J. Gorman, RRRE-31

Commandant
US Marine Corps
Code A04F
Washington 25, D. C.

Commander
US Naval Ordnance Laboratory
Technical Library
Corona, Calif

Commander
Naval Ordnance Laboratory
White Oak
Silver Spring, Md
ATTN: B. Gilbert

Commander
US Naval Ordnance Test Station
China Lake, Calif
ATTN: Tech Library

Director
US Naval Research Laboratory
Washington 25, D. C.
ATTN: Code 2027

Aeronautical Systems Division
Wright-Patterson AFB, Ohio
ATTN: ASRMOD (M. Shorr)

Air Force Special Weapon Center
Kirtland Air Force Base
Albuquerque, New Mexico
ATTN: Tech Library - SW01

Commander
Air Proving Ground Ctr
Eglin AFB, Florida
ATTN: Library - APGC (PGAPI)

Commander
Edwards Air Force Base
Edwards Air Force Base, Calif
ATTN: M. Jones AFTTC (FTOOT)

Commander
Armed Forces Tech Info Agency
Arlington Hall Station
Arlington 12, Virginia
ATTN: TIPDR (10 copies)

DISTRIBUTION (Cont'd)

Sandia Corporation
Sandia Base
Albuquerque, New Mexico
ATTN: Tech Library

Atomic Energy Commission
Space Nuclear Propulsion Office
Washington 25, D. C.
ATTN: F. C. Schwenk

US Atomic Energy Commission
Hdqtrs Library
Washington 25, D. C.

Franklin Institute of the
State of Pennsylvania
Philadelphia 5, Pennsylvania
ATTN: C.W. Hargens, Tech Dir
ATTN: Charles A. Belsterling

Library of Congress
Science & Technology Div
Washington 25, D. C.

Los Alamos Scientific Laboratory
P. O. Box 1663
Los Alamos, New Mexico
ATTN: Report Librarian

Marshall Space Flight Center
Computation Division
Huntsville, Alabama
ATTN: Dr. Walter P. Krause

NASA
Langley Research Center
Langley Station
Hampton, Va
ATTN: Tech Library

National Aeronautics & Space Agency
Lewis Research Center
Cleveland 35, Ohio
ATTN: K. Hiller

NASA Representative
Scientific Info Facility
P. O. Box 5700
Bethesda, Md
ATTN: S-AK-RKT-3799

National Bureau of Standards
Washington 25, D. C.
ATTN: Library

National Bureau of Standards
Boulder, Colorado
ATTN: Tech Library

National Bureau of Standards
Washington 25, D. C.
ATTN: Chief Sec 14.01
Bldg 16 Rm 310

Patent Office
Washington 25, D. C.
ATTN: Scientific Library
Acquisitions, Rm. 1886-C

University of Arizona
Physics Department
Tucson, Arizona
ATTN: Prof Ulrich H. Bents

Armour Research Foundation of
Illinois Ins. of Tech. Center
Chicago 16, Illinois
ATTN: George I. Jacobi
10 W. 35th Street

University of California
Engineering Library
Berkeley 4, Calif

Carnegie Institute of Technology
Pittsburgh, Pa
ATTN: Tech Library
ATTN: Dr. E. M. Williams

Cornell University
Ithaca, N. Y.
ATTN: Dr. Edward Resler, Jr.

Engineering Societies Library
345 East 47th Street
New York 17, N. Y.

Johns Hopkins University
Applied Physics Lab.
8621 Georgia Ave
Silver Spring, Md
Attn: Tech Lib - 2 copies - B

Distribution (Cont'd)

Linda Hall Library
5109 Cherry Street
Kansas City 10, Mo
ATTN: Joseph C. Shipman

University of Maryland
College of Aero Engineering
College Park, Maryland
Attn: W. Sherwood

University of Maryland
Director, Wind Tunnel
College Park, Md
ATTN: Mr. Donald S. Gross

Mass. Inst of Technology
Dept of Mech Engineering
Cambridge, Mass
ATTN: J. L. Shearer - B Rm 3-453

University of New Mexico
Albuquerque, N. M.
ATTN: Dr. A.H. Koschmann

New York State University
School of Engineering
6 Chemistry Road
Buffalo 14, N. Y.
ATTN: Tech Library

Ohio State University
576 Melrose Ave
Columbus 2, Ohio
ATTN: Tech Library

Rutgers State University
University Library
New Brunswick, N. J.
ATTN: Dr. D. F. Cameron

INTERNAL

Horton, B.M./McEvoy, R.W., Lt Col

Apstein, M./Gerwin, H.L./Guarino, P.A./Kalmus, H. P.

Spates, J. E./Schwenk, C.C.

Hardin, C. D., Lab 100

Sommer, H., Lab 200

Hatcher, R.D., Lab 300

Hoff, R.S., Lab 400

Nilson, H., Lab 500

Flyer, I.N., Lab 600

Campagna, J.H./Apolenis, C.J., Div 700

DeMasi, R., Div 800

Landis, P.E./Lab 900

Seaton, J.W., 260

Keller, C., 300

Kirshner, J., 310 (15 copies)

Warren, R., 310

Woodward, K., 310

Burton, W., 310

Carter, V., 310

Campagnuolo, C.J., 310

Cuneo, J., 310

Deadwyler, R., 310

Dockery, R., 310

Fine, J., 310

Foxwell, J., 310

Gaylord, W., 310

Goto, J., 310

Gotttron, R., 310

Holmes, A., 310

Iseman, J., 310

Joyce, J., 310

Katz, S., 310

Keto, J., 310

Marsh, D., 310

Mon, G., 310

Palmisano, R., 310

Straub, H., 310

Spyropoulos, C., 310

Ravilious, E., 310

Roffman, G., 310

Toda, K., 310

Talkin, A., 310

Wayne, S., 310

Wright, E., 310

Rotkin, I./Godfrey, T.B./Eichberg, R.L.

Bryant, W.T./Distad, M.F./McCoskey, R.E./Moorhead, J.G.

Eisenberger, N., 310

Garver, R. V., 250

Scudder, K. R., 310

Wagner, S. C., 310

Harris, F. T., 320

Hobbs, E. V., 310

Tech Reports Unit, 800 - 5 copies

Tech Info Office, 010 - 10 copies

HDL Library - 5 copies

AD _____ UNCLASSIFIED _____ ACCESSION NO. _____

Harry Diamond Laboratories, Washington 25, D. C.
Pneumatic Devices—
Design, Amplifier
Casting—Plastics

FLUID AMPLIFICATION—8. Use of Epoxy Castings for Fluid Amplifier Design - David S. Marsh and Edward V. Hobbs
TR-1102, 11 February 1963, 10 pp text, 5 pp illus, DA-5803-01-003
ONS 5010.11.71200, EML Proj. 31100, UNCLASSIFIED Report

An adjustable master unit has been used to make series of cast-epoxy fluid amplifiers that incorporate incremental dimensional changes. Subsequent unit testing identifies the best geometry for a given performance requirement. The process provides an inexpensive means of precisely producing the numerous units necessary for empirical design studies.

The basic rubber mold and epoxy casting process is described, as well as the adjustment of the master unit. Some other uses of epoxy castings in the fluid amplifier field are also described.

UNCLASSIFIED

AD _____ UNCLASSIFIED _____ ACCESSION NO. _____

Harry Diamond Laboratories, Washington 25, D. C.
Pneumatic Devices—
Design, Amplifier
Casting—Plastics

FLUID AMPLIFICATION—8. Use of Epoxy Castings for Fluid Amplifier Design - David S. Marsh and Edward V. Hobbs
TR-1102, 11 February 1963, 10 pp text, 5 pp illus, DA-5803-01-003
ONS 5010.11.71200, EML Proj. 31100, UNCLASSIFIED Report

An adjustable master unit has been used to make series of cast-epoxy fluid amplifiers that incorporate incremental dimensional changes. Subsequent unit testing identifies the best geometry for a given performance requirement. The process provides an inexpensive means of precisely producing the numerous units necessary for empirical design studies.

The basic rubber mold and epoxy casting process is described, as well as the adjustment of the master unit. Some other uses of epoxy castings in the fluid amplifier field are also described.

UNCLASSIFIED

AD _____ UNCLASSIFIED _____ ACCESSION NO. _____

Harry Diamond Laboratories, Washington 25, D. C.
Pneumatic Devices—
Design, Amplifier
Casting—Plastics

FLUID AMPLIFICATION—8. Use of Epoxy Castings for Fluid Amplifier Design - David S. Marsh and Edward V. Hobbs
TR-1102, 11 February 1963, 10 pp text, 5 pp illus, DA-5803-01-003
ONS 5010.11.71200, EML Proj. 31100, UNCLASSIFIED Report

An adjustable master unit has been used to make series of cast-epoxy fluid amplifiers that incorporate incremental dimensional changes. Subsequent unit testing identifies the best geometry for a given performance requirement. The process provides an inexpensive means of precisely producing the numerous units necessary for empirical design studies.

The basic rubber mold and epoxy casting process is described, as well as the adjustment of the master unit. Some other uses of epoxy castings in the fluid amplifier field are also described.

UNCLASSIFIED

AD _____ UNCLASSIFIED _____ ACCESSION NO. _____

Harry Diamond Laboratories, Washington 25, D. C.
Pneumatic Devices—
Design, Amplifier
Casting—Plastics

FLUID AMPLIFICATION—8. Use of Epoxy Castings for Fluid Amplifier Design - David S. Marsh and Edward V. Hobbs
TR-1102, 11 February 1963, 10 pp text, 5 pp illus, DA-5803-01-003
ONS 5010.11.71200, EML Proj. 31100, UNCLASSIFIED Report

An adjustable master unit has been used to make series of cast-epoxy fluid amplifiers that incorporate incremental dimensional changes. Subsequent unit testing identifies the best geometry for a given performance requirement. The process provides an inexpensive means of precisely producing the numerous units necessary for empirical design studies.

The basic rubber mold and epoxy casting process is described, as well as the adjustment of the master unit. Some other uses of epoxy castings in the fluid amplifier field are also described.

UNCLASSIFIED

REMOVAL OF EACH CARD WILL BE NOTED ON INSIDE BACK COVER, AND REMOVED CARDS WILL BE TREATED AS REQUIRED BY THEIR SECURITY CLASSIFICATION.